## **Cationic Bitumen (Asphalt) Emulsion**

**Type: Rapid-Setting** 

**Grade: CRS-2** 

**Standard: ASTM D 2397M - 13** 



Property	Min	Max	Test Method
Test on Emulsions			
Viscosity, Saybolt Furol at 50 °C, SFS	-	400	ASTM D244
Storage stability test, 24-h, %	-	1	ASTM D6930
Demulsibility, 35 mL, 0.8 % dioctyl sodium sulfosuccinate, %	20	-	ASTM D6936
Particle charge test	positive		ASTM D244
Sieve test, %	-	0.1	ASTM D6933
Distillation:			
Oil distillate, by volume of emulsion, %	-	3	ASTM D6997
Residue, %	65	-	ASTM D244
Tests on residue from distillation test:			
Penetration, 25°C (77°F), 100 g, 5 s	40	250	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	20	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042