

Cationic Bitumen (Asphalt) Emulsion

Type : Slow-Setting

Grade : CSS-1h

Standard : ASTM D 2397M - 13



Property	Min	Max	Test Method
Test on Emulsions			
Viscosity, Saybolt Furol at 25 °C, SFS	-	100	ASTM D244
Storage stability test, 24-h, %	-	1	ASTM D6930
Particle charge test	positive		ASTM D244
Sieve test, %	-	0.1	ASTM D6933
Cement mixing test, %		3.0	ASTM D6935
Distillation:			
Residue, %	57	-	ASTM D244
Tests on residue from distillation test:			
Penetration, 25°C (77°F), 100 g, 5 s	30	250	ASTM D5
Ductility, 25°C (77°F), 5 cm/min, cm	20	-	ASTM D113
Solubility in trichloroethylene, %	97.5	-	ASTM D2042