

## Cutback Bitumen

Type : Medium-Curing

Grade : MC-3000

Standard : ASTM D 2027M - 13



Property	Min	Max	Test Method
Kinematic viscosity at 60°C mm <sup>2</sup> /s	3000	6000	ASTM D2170
Flash Point (Tag Open-Cup), °C	60	-	ASTM D3143
Distillate test:			
Distillate, volume percent of total Distillate to 360°C:			
To 225°C	-	-	ASTM D402
To 260°C	-	20	ASTM D402
To 316°C	-	80	ASTM D402
Residue from distillation to 360°C, percent volume by difference	80	-	ASTM D402
Tests on residue from distillation:			
Viscosity at 60 °C,	20	120	ASTM D2170
Penetration at 25 °C,	70	250	ASTM D5
Ductility at 25 °C,	50	-	ASTM D113
Solubility in trichloroethylene, %	99	-	ASTM D2042
Water, %	-	0.2	ASTM D95