

Cutback Bitumen

Type : Slow-Curing

Grade : SC-70

Standard : ASTM D 2026M - 15



Property	Min	Max	Test Method
Kinematic viscosity at 60°C [140°F], mm ² /s	70	140	ASTM D2170
Flash point (Cleveland open cup), °C [°F]	60	-	ASTM D92
Distillate test:			
Total distillate to 360°C [680°F], volume %	-	35	ASTM D402
Solubility, %	95		ASTM D2042
Kinematic viscosity on distillation residue at 60°C [140°F], mm ² /s	200	7000	ASTM D2170
Asphalt residue:			
Residue of 100 penetration, %	40		ASTM D243
Ductility of 100 penetration residue at 25°C [77°F], cm	50		ASTM D113
Water, %	-	0.5	ASTM D95